



# **G. D. KOUTLIS S.A.**

## **MANUFACTURERS OF PAINTS & VARNISHES**

**FACTORY:** 34<sup>th</sup> km ATHENS/LAMIA NATIONAL ROAD

(OROPOS/MARCOPOULO CROSSING),

GR-19011 POLYDENDRI ATTIKIS, GREECE.

**PHONES:** +30-22950-22146 (5 lines) / **FAX :** +30-22950-22124

<http://www.erlac.gr>, e-mail: support@erlac.gr – exports@erlac.gr

---

## **ER-LUX** **SYNTHETIC ENAMEL PAINT**

### **GENERAL CHARACTERISTICS**

Alkyd-resin-based enamel paint for painting and protection of wooden and metal surfaces.

Applies easily, has good leveling, high gloss and outstanding coverage.

It has excellent adhesion without crackings. It is yellowing resistant under rough weathering conditions and retains gloss and unfading shades for a long time.

It has exceptional resistance to rough weather conditions, washing and air pollution.

It is lead and chromic free.

### **APPLICATION**

**Surfaces to apply:** Metallic and wooden.

**Preparation:** Antirust undercoat RUST PRIMER for metallic surfaces.

Wood primer VELATURA for wooden surfaces.

**Application:** Applies with brush or roller diluted until 3% by volume with solvent White Spirit WS-100. Sand the wooden surfaces before application with sandpaper No 320.

**The product is subject to directive 2004/42/E.C.**

Category A/d (interior/exterior trim and cladding paints for wood, metal or plastic) – Type Solvent based - Limit V.O.C. value : 400 gr/lt (2007), 300 gr/lt (2010).

V.O.C. maximum for this product ready for use: 395 gr/lt.

### **TECHNICAL DATA**

**Color:** White, black, all the shades of COLORMIX system and ER-LUX colour selector.

**Viscosity:** 200-230 sec (Ford Cup No 4).

**Specific Gravity:** 0,95-1,25 gr/ml.

**Thinning:** Until 3% by volume with solvent White Spirit WS-100 for roller and brush application,

**Gloss degree at 60°:** a) Gloss 80-95%, b) Satin 35-50 %, c) Mat 5-20%.

**Drying Time:** Touch free: 4-6 hours, Dry Trough: 16-24 hours.

**Theoretical coverage:** 10-12 m<sup>2</sup>/lt.

**Packing:** White, Black and ready shades: 0.375, 0.75, 2.5 lt.  
Bases: 1. 3 lt.