



# **G. D. KOUTLIS S.A.**

## **MANUFACTURERS OF PAINTS & VARNISHES**

**FACTORY:** 34<sup>th</sup> km ATHENS/LAMIA NATIONAL ROAD

**(OROPOS/MARCOPOULO CROSSING),**

GR-19011 POLYDENDRI ATTIKIS , GREECE.

**PHONES:** +30-22950-22146 (5 lines) / **FAX :** +30-22950-22124

<http://www.erlac.gr>, **e-mail:** support@erlac.gr – exports@erlac.gr

---

## **STONY S-81**

### **GENERAL CHARACTERISTICS**

Colorless, waterproof, 1-component varnish, for decoration and protection of any kind of stones. Suitable for the decoration and protection of walls and fireplaces made out of stones, bricks, tiles and other decorative building materials made out of concrete. It penetrates the pores and shows the colors.

It protects the stones from rough weathering conditions and humidity.

It has non-yellowing and non-stripping properties, it is impact and friction resistant and protects from solar radiation. It can be refinished with the same material, without prior grinding.

### **APPLICATION**

**Surfaces to apply:** It is suggested for stones, marbles, bricks, tiles and all the stony wall coatings indoor and outdoor such as building frontages e.t.c..

**Preparation:** Clean well the surface from any dirt, dust, oil, fat, wax, e.t.c..

**Application:** Apply with spray gun brush or roller without diluting in two layers.

The product is subject to directive 2004/42/E.C.

Category A/h “Binding Primers – Type Solvent based”.

Limit V.O.C. value : 750 gr/lit (2007), 750 gr/lit (2010).

V.O.C. maximum for this product ready for use : 740gr/lit.

### **TECHNICAL DATA**

**Specific Gravity:** 0,95 gr/ml.

**Viscosity 20° C:** 15-25 sec ( Ford Cup 4 ).

**Thinning:** Ready for use.

**Drying Time:** Dust free: 10 min

Touch free: 25 min.

Dry trough: 2-3 hours. Depends on the absorption capability of the surface.

**Recoatable:** 3 hours.

**Theoretical coverage:** 6-8 m<sup>2</sup>/lit.

**Packing:** 0,75, 2,5 lt.