



# **G. D. KOUTLIS S.A.**

## **MANUFACTURERS OF PAINTS & VARNISHES**

**FACTORY:** 34<sup>th</sup> km ATHENS/LAMIA NATIONAL ROAD

(OROPOS/MARCOPOULO CROSSING),

GR-19011 POLYDENDRI ATTIKIS , GREECE.

**PHONES:** +30-22950-22146 (5 lines) / **FAX :** +30-22950-22124

<http://www.erlac.gr>, **e-mail:** support@erlac.gr – exports@erlac.gr

---

## **ER-PLAST** **EMULSION PAINT**

### **GENERAL CHARACTERISTICS**

Water-diluted paint, suitable for painting and protection of indoor/outdoor building surfaces.

It provides high coverage and very good coating spread.

It provides vivid whiteness, excellent adhesion and elasticity, is yellowing resistant and does not flake off.

Full mechanical resistance after 3 weeks and then washable. Excellent resistance in washing and rough weather conditions.

### **APPLICATION**

**Surfaces to apply:** Drying and clean old and new plasters, concrete, cement, gypsumboard etc.

**Preparation:** With Emulsion Paint Primer or undercoat Monodur or Er-Plast diluted 40% with water. For alkalic surfaces it demanded acrylic-based undercoat.

**Application:** Applies with roller or brush diluted 10-20% with water on very good cleaned surfaces.

Avoid application when environmental temperature is less than 5°C or higher than 40°C.

**The product is subject to directive 2004/42/E.C.**

**Category A/a “Interior matt walls and ceilings. - Type water based”. Limit V.O.C. value : 75 gr/lt (2007), 30 gr/lt (2010).**

**V.O.C. maximum for this product ready for use : 74gr/lt.**

### **TECHNICAL DATA**

**Color:** White and 1000 shades of COLORMIX system.

**Specific Gravity:** 1,45-1,55 gr/ml.

**Viscosity:** 8000-9000cP.

**Gloss:** Mat.

**Thinning:** 10-20% with water.

**Drying Time:** 1-2 hours.

**Recoatable:** 2-4 hours.

**Theoretical coverage:** 9-11 m<sup>2</sup>/lt.

**Packing:** 0.75, 3, 10 lt.