

WOODEX AQUA WOOD OIL

Wood oil

Water-borne wood oil for outdoor use.

Natural oil for outdoor use for protection of garden deck floors, jetties and wooden garden furniture.

Other suitable objects are fences, trellises, doors and stairs. For untreated, heat-treated and press-impregnated wood. Applied on clean, dry wooden surface by brush, sponge or by dipping. Protects wooden surfaces from moisture, soiling and when tinted from UV radiation of the sun. Deminishes cracking of the wooden surface.



TECHNICAL DATA

Certificates, approvals and classification	Finnish Key Flag
Fields of application	Decking, Fences, Garden furniture
Recommended substrate	Press-impregnated wood, Raw wood, Thermally modified wood
Solids	Approx. 10% by volume
Volatile organic compound (VOC)	The product is not included in the EU VOC directive.
Practical spreading rate	Sawn timber: 5 - 8 m ² /l. Planed timber: 8 - 10 m ² /l.
Colours	Clear, brown and grey. Can be tinted to translucent shades.
Tinting system	Teknomix
Gloss (60°)	Is absorbed into the wood and does not usually form any visible film.
Thinner	Water.
Density	Approx. 1 g/ml
Storage	Must not freeze.
Packaging	Clear, brown and grey: 0.9 l, 2.7 l, 9 l. Availability varies by country.

DIRECTION FOR USE

Surface preparation	Remove from the surface all loose matter, dirt, dust and brittle top layers of the wood with wire-brush, scrubbing brush or scraper. Clean the surface to be treated. Remove old paint or varnish layers before the treatment. Use RENSA TERRACE deck cleaner on surfaces to be treated, when needed. Rinse the surfaces thoroughly with water and allow to dry. Untreated new wood is primed with wood preservative from the WOODEX series.
----------------------------	---

Application method	Dipping, Brush, Sponge
Application	Stir thoroughly before use. Tinted product must also be stirred during the application, if needed. Apply once or twice. Depending on the quality of the wood, the treatment is renewed. The possible excess oil is wiped off. Reserve a sufficient amount of oil of the same batch for each uniform surface. Not suitable for greenhouses, hotbeds and shelters for livestock.
Application conditions	The surface to be treated must be dry. The moisture content of the wood is to be below 20%. During the application and drying period the temperature of the ambient air, the surface and the product shall be above +5°C and the relative air humidity below 80%. Application in strong sunlight or in moist weather is to be avoided. It is recommended that press-impregnated wood is let to dry for at least 6 months after the installation before it is treated.
Drying time	+23°C
- dust free	4 h
- dry to use	16 h
	Mechanical abrasion on the surface is to be avoided during the first few days. If a renewed treatment is required, it can be applied after about 24 hours. The drying process will be slower in cold and/or damp.
Cleaning	Warm water and RENSA BRUSH brush cleaner. Wash the equipment immediately after use.

HEALTH AND SAFETY

Safety and precaution measures	See safety data sheet. NOTE! Because of the danger of spontaneous combustion, any waste from the product, spray mist and soiled rags etc. are to be kept in a fire-proof place in air-tight containers. Immersion in water is also recommended.
---------------------------------------	--

ADDITIONAL INFORMATION

Maintenance instructions	For surfaces that are continuously exposed to weathering a renewed treatment is done yearly, or whenever required.
---------------------------------	--

Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.